



Scheda Tecnica Technical Specifications

Tipo/Code 1818 AS

Cartone grigio grigio accoppiato alto spessore bilucido

Both sides smooth grey pasteboard

Gramm. Substance	Spessore Thickness	Volume Bulk	Umidità Moisture	Rigidità Taber (7.5°) Taber stiffness (7.5°)	
				Longitudinale longitudinal	Trasversale Transversal
g/mq	mm	cm3		MD	CD
970	1.50	1.55	6.5%	3700	1100
1080	1.70	1.57	6.5%	4850	1560
1140	1.80	1.58	6.5%	5250	1740
1265	2.00	1.58	6.5%	6200	2300
1390	2.20	1.58	6.5%	6850	2560
1520	2.40	1.58	6.5%	8200	3780
1585	2.50	1.58	6.5%	>10000	4360
1890	3.00	1.58	6.5%		
2210	3.50	1.58	6.5%		
2520	4.00	1.59	6.5%		

Tolleranze Tolerances

Grammatura Substance +/- 5%

Umidità Moisture +/- 1%

Spessore/ Thickness +/- 5%

Rigidità/ Stiffness +/- 10%

Updating: 02/2019