

Technical Data Sheet



Property	Test Method	Unit	Tolerance	115	130	150	170
Substance	ISO 536 TAPPI T410	g/m ²	±4%	115	130	150	170
Thickness	ISO 534 TAPPI T411	µm	±4%	121	136	157	178
Bulk	ISO 534 TAPPI T411	cm ³ /g	-	1.05	1.05	1.05	1.09
Opacity	ISO 2471 TAPPI T519	%	-2.0	95.0	96.0	97.0	98.0
Whiteness D65/10°	ISO 11475	CIE	±3	119	119	119	119
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	12	12	12	12
Parker roughness	ISO 8791-4 TAPPI T555	µm	±1	4.0	4.0	4.0	4.0
Relative humidity	TAPPI T502	%	±7	50	50	50	50