

MG thin paper

Paper for flexible packaging

VELINA CF

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m2	20	22		
Gurley air permeability	ISO 5636-5	s	8	9		
Tearing strength MD	ISO 1974	mN	145	150		
Tearing strength CD	ISO 1974	mN	215	230		
Tearing strenght av.	ISO 1974	mN	180	190		
Burst resistance	ISO 2758	K Pa	36	42		

Tolerances	Ref. STD	Unit of meas.	RANGE			
Substance	ISO 536	g/m2	19/21	20.7/23.3		
Gurley air permeability	ISO 5636-5	s	6/10	6/12		
Tearing strength MD	ISO 1974	mN	125/165	130/170		
Tearing strength CD	ISO 1974	mN	185/245	200/265		
Tearing strenght av.	ISO 1974	mN	155/205	160/220		
Burst resistance	ISO 2758	K Pa	34/41	35/50		

Notes: POROSITA' GURLEY ESEGUITA SU 10 FOGLI
 Finishing **Machine Glazed**
 Printing method **Flexographic**
 Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.