



reacto®
CARBONLESS PAPER

reacto® CFB coated front and back

Selbstdurchschreibepapier, Mittelblatt, beidseitig gestrichen

Carbonless paper, middle sheet, coated on both sides

Papel autocopiativo, hoja intermedia, ambas caras recubiertas

Papier autocopiant, feuille intermédiaire, couché des deux côtés

Merkmal Property Propiedad Caractéristique	Prüfnorm Standard Norma Norme	Einheit Unit Unidad Unité	Wert Value Valor Valeur			Toleranz Tolerance Tolerancia Tolérance
			53	60	75	
Flächengewicht Basis weight Gramaje Grammage	ISO 536	g/m ² gsm	53	60	75	± 5 %
Dicke Caliper Calibre Epaisseur	ISO 534	µm	70	78	96	± 5
Glätte Bekk (OS) Smoothness Bekk (TS) Lisura Bekk anverso Lissé Bekk recto	ISO 5627	s	45			± 20
Weiß R457 Brightness R457 Blancura R457 Blancheur R457	ISO 2470	%	92			± 3
Reißlänge längs Breaking length md Longitud de rotura Longueur de rupture SM	ISO 1924-1	m	> 5.000			
Feuchte absolut Absolute humidity Humedad absoluta Humidité absolue		%	5,8			± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso / sous réserve de modifications



Koehler
PAPER

Koehler Paper SE

Hauptstraße 2 · 77704 Oberkirch · Germany · Phone +49 7802 81-0 · Fax +49 7802 81-4330 · www.koehlerpaper.com